

Low VOC Stain Blocking Paint

180 g/m²

FPS 452

	Weight, %	Suppliers
Water	15.00	
<i>Add in order under stirring</i>		
Natrosol Plus 330 PA	0.20	Ashland Aqualon
Tego Dispers 750 W	0.50	Tego Evonik
Foamaster 8034	0.20	Cognis
AB Rust A4	0.50	Labema
Kronos 2190	25.00	Kronos
Millisil C400	8.00	Sifraco
Optimat 2550	0.60	World Minerals
Water	5.00	
PlusTalc D 30 E	13.50	Mondo Minerals
<i>Disperse at high speed then add</i>		
Hydro PLIOLITE 050	30.00	ELIOKEM
<i>Mix well then add under stirring</i>		
Aquaflow NHS 300	0.80	Ashland Aqualon
Acticide MBS	0.20	Thor Biocides
Aquaflow XLS 525	0.30	Ashland Aqualon
Foamaster 8034	0.20	Cognis

PVC	51.8%	Specific Gravity	1.50
Volume Solids	40.5%	VOC (EU)	1.5 g/l
Weight Solids	60.2%	Viscosity @ 10 000 s ⁻¹	0.18 Pa.s

Directive 2004/42/EC : maximum VOC content
Cat. A/g : 50 g/l (2007)
30 g/l (2010)

FPS 452 / Jun 10 / NM